


Mixing MONSTASHADES™ with ML55 Tintable MONSTALINER™

(Clean 2 gallon plastic pail required)




Mix color with Tintable MONSTALINER™




Power mix contents of tintable coating for 3 full minutes before adding color. Dump Monstashades Color Concentrate into gallon and add 1 oz (2 tablespoons) of MEK or Acetone to the empty color can. Seal can and shake before dumping wash liquid into gallon. Power mix gallon with color for 4 to 5 minutes stopping at least 2 times to scrape sides and bottom of can with wooden mix stick.

Mix tinted coating together with Extreme Performance Catalyst in a clean 2 gallon plastic pail



- Dump contents of color mixed gallon into a clean 2 gallon plastic pail and scrape remaining material from gallon into pail.
- Shake Catalyst for 30 seconds and pour contents into color mixed material. Scrape remaining material from catalyst can.
- Power mix catalyst into Monstalinier/Monstashades mixture for 4 full minutes stopping occasionally to scrape container sides and bottom.

Pour mixed components back into original gallon can and stop ½ inch from top. Close lid tight.



DO NOT leave mixed material in plastic pail!

Use extra coating in mixing pail to start brushing corners & edges of your project then reopen gallon can to continue by pouring into roller pan

During installation of Colored Monstalinier, initial re-thickening will occur as a result of viscosity control agents used to create texture. This is normal and re-power mixing at any time in the first few hours will thin down material.

Never work directly from an open can. Pour sparingly into the roller pan. When first coat is complete pour 2 - 3 oz (4 - 6 tablespoons) of MEK or Acetone over surface of remaining coating in can. Seal lid tightly. Re-power mix when beginning 2nd coat.

